



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : A61L 2/18, B65B 55/10	A1	(11) International Publication Number: WO 94/01143 (43) International Publication Date: 20 January 1994 (20.01.94)
(21) International Application Number: PCT/SE93/00604 (22) International Filing Date: 30 June 1993 (30.06.93) (30) Priority data : 9202035-3 1 July 1992 (01.07.92) SE (71) Applicant (for all designated States except US): W.R. GRACE & CO.-CONN. [US/US]; 1114 Avenue of the Americas, New York, NY 10036 (US). (72) Inventors; and (75) Inventors/Applicants (for US only) : PAHLMARK, Kristian [SE/SE]; Bärnstensgatan 6, S-263 58 Höganäs (SE). PERSSON, Git [SE/SE]; Övre Eneborgsvägen 11 A, S-252 48 Helsingborg (SE).		(74) Agent: AWAPATENT AB; Box 45086, S-104 30 Stockholm (SE). (81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, US, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: STERILIZATION PROCESS AND COMPOSITION (57) Abstract <p>A process for the sterilization of the surface of a packaging material, e.g. a plastic coated board, by contacting said material with a hydrogen peroxide solution, said hydrogen peroxide solution being modified by the addition thereto of a penetration-reducing amount of a penetration-reducing salt. The salt referred to is preferably an alkali metal salt, for instance a sulphate or halogenide, such as sodium sulphate or sodium chloride. A composition which is useful for carrying said sterilization process into effect, which comprises a hydrogen peroxide solution with the addition of a penetration-reducing amount of a penetration-reducing salt.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TG	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

TITLE OF THE INVENTIONSTERILIZATION PROCESS AND COMPOSITION

5

TECHNICAL FIELD OF THE INVENTION

The present invention relates to the field of sterilization of packaging materials in connection with the use of said materials for the packaging of substances which must not be contaminated with microorganisms, for instance food stuffs and beverages. More specifically the invention is within the field of sterilization of such materials by means of hydrogen peroxide as the sterilization agent.

15 BACKGROUND OF THE INVENTION

For certain packaging material grades, especially such materials which are intended to be used for food stuffs, beverages, etc., a sterilization of the surface thereof is required in order to minimize the contribution of microorganisms from the packaging material to the product to be contained therein. One of said sterilization methods involves the use of hydrogen peroxide as the sterilization agent. There are different methods of applying said hydrogen peroxide to the packaging material, such as by passing the packaging material through the hydrogen peroxide, immersing said material in said hydrogen peroxide, applying a film of hydrogen peroxide to the surface of the packaging material, etc., but generally the hydrogen peroxide is utilized in the form of a solution thereof, especially an aqueous solution.

Although the packaging material has generally been made hydrofobic during the manufacture thereof, in order to make it resistant to the penetration of aqueous liquids, including a hydrogen peroxide solution, the hydrogen peroxide is usually utilized in such a concentration and at such a temperature that a penetration thereof into the packaging material is not easily avoided. The hot

aqueous hydrogen peroxide solution especially penetrates the edges of the packaging material, but also in a case where for some reason the packaging machine has to be stopped, there will be a great risk of having a penetration of the hot hydrogen peroxide into the packaging material to loosen up the same. When restarting the machine part of the packaging material has to be discarded or else there will be a risk of having a bursting of any package inside the machine which means a cleaning operation for several hours.

Thus, in summary, there is no available system today which will impart to the packaging material such a degree of hydrofobicity that a penetration of a concentrated and hot hydrogen peroxide solution is avoided.

15 OBJECT OF THE INVENTION

The main object of the present invention is to modify the previously known sterilization process where a solution of hydrogen peroxide is utilized to manufacture an aseptic packaging material so as to greatly reduce the penetration, especially the edge penetration, of the hydrogen peroxide solution into the packaging material. Other objects of the invention will be apparent to a person skilled in the art when reading the description of the present invention.

25 GENERAL DESCRIPTION OF THE INVENTION

According to the present invention it has been shown that the above-mentioned object can be achieved by the addition of a salt to the hydrogen peroxide solution, which salt counteracts the penetration of the hydrogen peroxide into the packaging material. Thus, in accordance with the present invention it has been found that said penetration may be decreased or reduced with at least 50%, which means a very significant improvement within the art of manufacturing aseptic packages, as said manufacturing takes place at very high rates and quantities.

More specifically the invention relates to a process for the sterilization of the surface of a packaging material by contacting said material with a hydrogen peroxide solution, characterized by modifying the hydrogen peroxide solution by the addition thereto of a penetration-reducing amount of a penetration-reducing salt.

The invention also relates to a composition which is useful for the sterilization of the surfaces of a packaging material of the type referred to, which comprises a hydrogen peroxide solution, characterized in that it comprises a penetration-reducing amount of a penetration-reducing salt.

DETAILED DESCRIPTION OF THE INVENTION

Generally the process according to the invention is applicable to the sterilization of any packaging material for which hydrogen peroxide solutions have been previously utilized. Especially interesting packaging materials in connection with the invention are, however, paper board and more specifically a hydrophobated board. With reference to hydrophobated board this generally means that the board has been coated with a hydrophobic film such as plastic or wax according to any known technique. Such packaging materials are for instance utilized in the packaging of different beverages, e.g. long life milk.

Now that the inventive idea has been disclosed it should be possible to a person skilled in the art to determine whether any salt will be useful for the practice of the invention or not. Generally, however, the requirement as to the penetration-reducing salt is that it is reasonably soluble in the hydrogen peroxide solution and that it does not catalyze the decomposition of the hydrogen peroxide to any substantial extent, i.e. not to such an extent that the sterilization effect is adversely influenced upon. Expressed in another way a suitable penetration-reducing salt for use in accordance with the invention includes any salt which reduces the penetration of a hydrogen peroxide sterilization solution into a hydro-

phobated board and which is compatible with the hydrogen peroxide solution is useful in accordance with the invention. Compatible in this sense may e.g. mean that the hydrogen peroxide concentration is not reduced to any substantial extent, for instance not more than 10%, or not more than 5%, during 1 week or even 2 weeks.

According to the invention it has been found that for instance alkali metal salts are preferable as to the non-penetration of the hydrogen peroxide. An especially preferable embodiment of the process of the invention means that a sodium salt is utilized.

Other potential salts for use in accordance with the invention may be selected from the group of alkaline earth metals, especially calcium and magnesium. Furthermore, aluminium salts should be useful in accordance with the invention.

According to another preferable embodiment of the invention the hydrogen peroxide solution is modified with a salt selected from the group consisting of sulphates and halogenides, preferably chlorides.

From the above-mentioned it can also be gathered that specifically interesting salts for the modification of the hydrogen peroxide solution are sodium sulphate and sodium chloride.

The salt referred to is generally used in a penetration-reducing amount, which should be easily determinable by a person skilled in the art, especially by means of the Wick index method which will be described more in detail below. However, a penetration-reducing amount of said salt is a concentration which reduces the Wick index of the paper board preferably by at least 20%, more preferably by at least 30% and most preferably by at least 40%. Generally, the solubility of the salt in hydrogen peroxide dictates the upper limit of the concentration range. However, in order to minimize the depositions of salts in the packaging machine a concentration as low as possible is aimed at. A preferable salt concentration may also be

defined as 0.5-1 mole/litre. Toxicity considerations should of course also be taken in the usual way when food stuffs and beverages are involved.

With reference to the contact between the packaging material and the hydrogen peroxide solution said contact is generally performed in accordance with the prior art, which preferably means that a hot aqueous hydrogen peroxide solution is used. The term hot is used in a broad meaning in accordance with the known technique, but according to a preferable embodiment of the process of the invention the temperature of the hydrogen peroxide solution is within the range of 50-80°C, especially good results being achieved at a temperature of the order of 70°C.

The concentration of the hydrogen peroxide solution, i.e. as to the contents thereof of H_2O_2 , is generally similar to that used according to the prior art. However, a preferable embodiment of the present invention involves the use of a solution that is 10-40% as to its hydrogen peroxide content, the percentage being calculated in accordance with current practice within this field. Especially preferable results are generally achieved with a hydrogen peroxide solution having a concentration of the order of 35%.

Also with reference to the pH-value of the hydrogen peroxide solution the general principles of the current art are applicable. Thus, also with the addition of the salt in accordance with the invention, which salt may well influence upon the pH of the solution, the previously known pH ranges are useful. Especially preferable results as to non-penetration in accordance with the invention are, however, obtained at a pH-value of the modified hydrogen peroxide solution within the range of 1-4, the range of 1.5-2.5 being especially preferable.

The contact between the packaging material and the modified hydrogen peroxide solution can take place in accordance with any one of the known techniques. Thus, in

this respect, reference is made to the prior art as concerns details of the different techniques utilized. According to a preferable embodiment of the process claimed the packaging material is, however, contacted with the hydrogen peroxide solution by passing the material there-
5 through in a continuous way.

Preferable embodiments of the composition according to the invention are the same as have been described in connection with the process claimed and will not be re-
10 peated here.

The process as well as the composition according to the invention will now be more specifically illustrated by means of the following non-limiting examples.

EXAMPLES

15 142 g of sodium sulphate were added to one litre of hydrogen peroxide. The concentration of the hydrogen peroxide was adjusted to 35%.

A plastic coated board was prepared and immersed into hot (70°C) hydrogen peroxide solution for 10 minutes and
20 the amount of liquid which had penetrated into the board was determined in accordance with the edge wicking method that will be described below and expressed as the Wick index. The Wick index was found to be 0.5 kg/m^2 which should be compared to a corresponding Wick index value of
25 0.9 kg/m^2 for a control (i.e. without any addition of salt).

The above experiment was repeated with sodium chloride in different concentrations. The addition of the salt means that the concentration or percentage of the hydrogen peroxide is reduced, and in addition thereto it was
30 found that the pH decreased. Therefore, if the specifications for the Wick test are to be followed one has to start from a hydrogen peroxide having a higher concentration than the one desired and optionally adjust the concentration and pH after the addition of the salt. The
35 solutions tested are presented in Table 1. Furthermore, NaHCO_3 was also tested but a slow evolution of gas was

7

noted which indicates that it catalyzes the decomposition of the hydrogen peroxide. Thus, the test with NaHCO_3 was discontinued.

5 TABLE 1

	<u>Test</u>	<u>Weight %</u>	<u>pH</u>
	35% H_2O_2	36.0	2.30
	+1.0 M NaCl	34.1	1.64
10	+2.0 M NaCl	32.4	1.60
	+3.0 M NaCl	30.7	1.49

With the above-mentioned solutions the edge penetration measurements were made, and in Table 2 the results
15 thereof are presented.

TABLE 2

	<u>Test</u>	<u>Wick (I)</u> (kg/m^2)	<u>Wick (II)</u> (kg/m^2)
	35% H_2O_2	1.15	0.96
	+1.0 M NaCl	0.79	0.66
25	+2.0 M NaCl	0.65	0.52
	+3.0 M NaCl	0.55	0.45

In this case Wick (I) means that the pH-value was not adjusted after the salt addition while Wick (II) refers to
30 such a pH adjustment. As is clear from this table the adjustment of the pH was of marginal influence only.

In order to investigate the effects of the dilutions obtained by the salt additions some experiments were made where the 36% hydrogen peroxide was diluted to 34% and
35 30%, respectively. The results thereof are presented in Table 3.

TABLE 3

	<u>Conc.</u> (%)	<u>Wick</u> (kg/m ²)
5		
	36	0.91
	34	0.88
	30	0.81

10

As can be seen the effect of a lower hydrogen peroxide concentration is a lower Wick value. The value obtained for 30% hydrogen peroxide should be compared to the value obtained with 3M NaCl (0.45-0.55 kg/m²).

15 Then the effects of NaCl with a proper hydrogen peroxide concentration (35%) and with adjusted pH values were investigated. The results thereof are presented in Table 4.

20 TABLE 4

	<u>Test</u>	<u>Wick</u> (kg/m ²)
25	Blank 35%	0.92
	+2M NaCl	0.61
	+3M NaCl	0.57

30 As is clear from the above Table the results for added salts are significantly superior also when the hydrogen peroxide concentration is the proper one according to the test method.

The first result presented above with reference to sodium sulphate was supplemented with additional results
35 as to sodium sulphate in accordance with Table 5 below.

TABLE 5

	<u>Test</u>	<u>Conc.</u> (%)	<u>Wick</u> (kg/m ²)	<u>pH</u>
5	Blank	35	0.91	2.4
	1M Na ₂ SO ₄	31.8	0.57	2.8 direct
	1M Na ₂ SO ₄	31.8	0.49	2.4 adjusted pH
10	1M Na ₂ SO ₄	35.0	0.49	2.4

As can be seen from the above-mentioned Table, contrary to what was obtained by the addition of sodium chloride, the pH value increased by the addition of the sulphate. Furthermore, it can be seen that the effect on the Wick value is higher with the sodium sulphate. Thus, with 1M Na₂SO₄ the result is similar to that obtained with 3M NaCl.

Different other salts were also tested in a way similar to that described above. The results thereof as to decomposition of hydrogen peroxide are presented in Table 6, the concentration being chosen so as to obtain an ionic strength of 3.0.

10

TABLE 6

	<u>Salt</u>	<u>Conc.</u> (M)	<u>Conc.</u>	<u>Conc. 1 week</u>	<u>Conc. 2 weeks</u>
			<u>directly</u> (% by weight of H_2O_2)	(% by weight of H_2O_2)	(% by weight of H_2O_2)
5					
	$Na_4P_2O_7$	0.3	47.0	---	43.6
	Na Acetate	3.0	33.8	---	31.1
10	$CaCl_2$	1.0	44.4	---	42.2
	Alum*	0.2	44.4	---	0.5
	Na_2SO_4	0.5	34.9	34.9	---
	Na_2SO_4	1.0	44.7	44.5	---
	Na_2SO_4	2.0	39.9	39.8	---
15					
	* $Al_2(SO_4)_3$				

Also Na_3PO_4 was tested but said test was discontinued due to gas evolution indicating the decomposition of the hydrogen peroxide.

As is clear from Table 6 the decomposition of the hydrogen peroxide varies to a great extent with the different salts used. The bad result obtained with alum is probably due to the presence of iron therein.

The effects of the salts above, except for alum were tested at 70°C with the hydrogen peroxide concentration adjusted to 35%. As is seen in Table 6 above the hydrogen peroxide concentration falls below 35% if 3.0M Na acetate is used. As 50% hydrogen peroxide was initially used, it was not possible to use more than 2.76 moles per liter of sodium acetate.

The results are presented in Table 7.

35

TABLE 7

	<u>Salt</u>	<u>Conc.</u> (M)	<u>Wick</u> (g/m ²)
5	Na ₄ P ₂ O ₇	0.3	1.6
	Na Acetate	2.76	1.8
	CaCl ₂	1.0	0.86
	Na ₂ SO ₄	0.5	0.85
10	Na ₂ SO ₄	1.0	0.55
	Na ₂ SO ₄	2.0	0.54
	Blank	---	1.5

One test was also made at 60°C, viz. with 1 M of Na₂SO₄. The result was comparable to that obtained at 70°C (Table 6 above).

Finally, with reference to the Wick values referred to above, the following test method was used.

EDGE WICKING OF SIZED PAPER AND PAPER BOARD
(70°C, 10 min 35% hydrogen peroxide)

DEFINITION

The edge wicking test is a method to determine how well a paper is sized against the specified test solution.

The edge wicking index (EWI) in this test is defined as the amount of liquid absorbed by the edges of test pieces placed for 10 minutes in hydrogen peroxide (H₂O₂).

The result is given in kg/m² and the testing conditions (time and temperature) must be reported.

EQUIPMENT

- water bath with thermostat
- analytical balance (with readability of 0.1 mg)
- guillotine
- stop watch
- tape, water resistant e.g. Scotch El-tape No. 5 from 3M Co

12

- dish, e.g. crystallizing dish of Duran glass
- rods of glass or stainless steel
- measuring glass
- beaker
- 5 - blotting paper
- thermometer (with readability of 1°C)

TEST SOLUTION

Hydrogen peroxide (Food grade) 35% by weight. Density
1130 kg/m³. pH 1.5 to 2.5. (same quality as used in AB8
10 and AB9).

TEST PROCEDURE

1. Preparation of test pieces

The raw paper should be conditioned according to
TP 85013 (modified SCAN P2:75).

15 TP 85013 specifies:

Preconditioning at 60°C for 30 minutes and the
conditioning at 23°C ± 1°C and 50% RH ± 2% RH for
at least 3 hours.

20 For raw paper cover the printing and the back
sides of the test material carefully with water
resistant tape. Make sure there are no air bubbles
between the paper and the tape.

25 For laminated material tape is not necessary. Cut
out 10 test pieces. Two (2) series with five (5)
test samples in each. The test pieces should be
25 mm (MD) x 75 mm (CD).

Please note that the cutting edges of the guillo-
tine must be sharp in order to get well cut edges.
The edges must be pressed against each other and
30 the test piece removed before the cutting edges
are separated, otherwise the fibre structure of
the edges can be disturbed.

2. Thickness measurement

35 Measure the thickness of the sample. For laminated
material, the thickness for polyethylen and alumi-
num foil should be subtracted.

13

Only the paper thickness is needed.

A mean value of the thickness for five test pieces should be used in the calculations.

3. Edge wicking test

5 Weigh each series of five (5) test pieces together up to the nearest mg on an analytical balance. At least two (2) series are preferable.

10 Pour hydrogen peroxide in a flat bottomed glass dish. Place the glass dish in a water bath and wait until the hydrogen peroxide has reached $70^{\circ}\text{C} \pm 1^{\circ}\text{C}$.

15 Place the test pieces in the glass dish so they do not touch each other and put glass rods on top. Make sure that the test pieces are covered by $10\text{ mm} \pm 1\text{ mm}$ of hydrogen peroxide.

20 Remove the test pieces after 10 minutes \pm 15 seconds and place them between two blotting papers and wipe off excessive liquid. Avoid hard pressing on the surface and avoid touching the edges. During these operations wear gloves and safety glasses (see Appendix 1).

The water bath with the peroxide should preferably be placed in a closed hood or under a well ventilated hood.

25 Weigh at once each series of five (5) test pieces together up to the nearest mg.

Note:

30 Hydrogen peroxide may evaporate during tests. Hence, it is necessary to add more hydrogen peroxide so the test pieces always are covered with $10\text{ mm} \pm 1\text{ mm}$ of liquid.

Start every day's measurements with fresh solution of hydrogen peroxide.

35

14

CALCULATION

W_1 = weight before (mg) contact with hydrogen peroxide

W_2 = weight after (mg) contact with hydrogen peroxide

5 t = thickness (μm), a mean value for five (5) test pieces

λ = sample edge length (m) 1 m

10
$$\text{Edge wicking index} = \frac{W_2 - W_1}{\lambda \times t}$$

For each series of five (5) test pieces:

15
$$\lambda = 1, \text{ i.e. } 5 \times (75 \text{ mm} + 75 \text{ mm} + 25 \text{ mm} + 25 \text{ mm}) = 1000 \text{ mm} = 1 \text{ m}$$

20
$$\text{Edge wicking index (EWI)} = \frac{W_2 - W_1 \text{ (mg)}}{t \text{ (}\mu\text{m)} \times 1 \text{ m}}$$

which gives a value in the unit kg/m^2

Remark 1

25 If the thickness of the base board is unknown
the edge wicking value (EWV) should be reported as mg/m.

Hence, for each series of five (5) test pieces

30
$$\lambda = 1, \text{ i.e. } 5 \times (75 \text{ mm} + 75 \text{ mm} + 25 \text{ mm} + 25 \text{ mm}) = 1000 \text{ mm} = 1 \text{ m}$$

35
$$\text{Edge wicking value (EWV)} = \frac{W_2 - W_1 \text{ (mg)}}{1 \text{ m}} \quad [\text{mg/m}]$$

15

Result

The edge wicking index will be reported in kg/m^2 .

Temperature and time must be specified.

If two or more series are carried out, a mean value should be reported.

5

10

15

20

25

30

35

CLAIMS

1. A process for the sterilization of the surfaces of a packaging material, especially board and more specifically hydrophobated, e.g. plastic coated, board, by contacting said material with a hydrogen peroxide solution, characterized by modifying the hydrogen peroxide solution by the addition thereto of a penetration-reducing amount of a penetration-reducing salt.

2. A process according to claim 1, characterized by modifying the hydrogen peroxide solution with an alkali metal salt, preferably a sodium salt.

3. A process according to claim 1, characterized by modifying the hydrogen peroxide solution with an alkaline earth metal salt, preferably a calcium or magnesium salt, or an aluminium salt.

4. A process according to any one of claims 1, 2 and 3, characterized by modifying the hydrogen peroxide solution with a salt selected from the group consisting of sulphates and halogenides, preferably chlorides.

5. A process according to any one of the preceding claims, characterized by modifying the hydrogen peroxide solution with Na_2SO_4 or NaCl .

6. A process according to any one of the preceding claims, characterized by modifying the hydrogen peroxide solution with said salt in an amount which reduces the Wick index by at least 20%, more preferably at least 30% and most preferably at least 40%, relative to the Wick index obtained without the addition of said salt.

7. A process according to any one of the preceding claims, characterized by contacting said material with a modified hot aqueous hydrogen peroxide solution, preferably with a temperature within the range of 50-80°C, especially around 70°C.

8. A process according to any one of the preceding claims, characterized by contacting said material with a modified 10-40%, preferably around 35%, hydrogen peroxide solution.

9. A process according to any one of the preceding claims, characterized by contacting said material with a modified hydrogen peroxide solution, the pH of which is within the range of 1-4, preferably 1.5-2.5.

5 10. A process according to any one of the preceding claims, characterized by contacting said material with the hydrogen peroxide solution by passing the material there-through, preferably in a continuous way.

10 11. A composition which is useful for the sterilization of the surfaces of a packaging material, especially board and more specifically hydrophobated, e.g. plastic coated board, comprising a hydrogen peroxide solution, characterized in that it comprises a penetration-reducing amount of a penetration-reducing salt.

15 12. A composition according to claim 11, characterized in that the penetration-reducing salt is an alkali metal salt, preferably a sodium salt.

20 13. A composition according to claim 11, characterized in that the penetration-reducing salt is an alkaline earth metal salt, preferably a calcium or magnesium salt, or an aluminium salt.

25 14. A composition according to any one of claims 11-13, characterized in that the penetration-reducing salt is selected from the group consisting of sulphates and halogenides, preferably chlorides.

15. A composition according to any one of claims 11-14, characterized in that the penetration-reducing salt is Na_2SO_4 or NaCl .

30 16. A composition according to any one of claims 11-15, characterized in that the penetration-reducing salt is present in an amount which reduces the Wick index by at least 20%, more preferably at least 30% and most preferably at least 40%.

35 17. A composition according to any one of claims 11-16, characterized in that the hydrogen peroxide content is 10-40%.

18

18. A composition according to any one of claims 11-17, characterized in that the hydrogen peroxide solution has a pH within the range of 1-4, preferably 1.5-2.5.

5

10

15

20

25

30

35

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 93/00604

A. CLASSIFICATION OF SUBJECT MATTER		
IPC5: A61L 2/18, B65B 55/10 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
IPC5: A61L, B65B		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
SE,DK,FI,NO classes as above		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB, A, 1099293 (TEPAR A.G.), 17 January 1968 (17.01.68), page 2, line 108 - line 115, claims 1-3 --	1,4,6-8, 10-11,14, 16-17
A	Chemical Abstracts, Volume 98, No 7, 14 February 1983 (14.02.83), (Columbus, Ohio, USA), page 538, THE ABSTRACT No 52223t, JP, A2, 57153873, (KOKAI TOKKYO KOHO) 22 Sept 1982 (22.09.82) --	1-18
P,A	WO, A1, 9219287 (SOLVAY INTEROX LIMITED), 12 November 1992 (12.11.92), page 4, line 2 - line 9; page 4, line 34 - line 38 -- -----	1-18
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input checked="" type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "B" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
28 Sept 1993		05 -10- 1993
Name and mailing address of the ISA/ Swedish Patent Office Box 5055, S-102 42 STOCKHOLM Facsimile No. +46 8 666 02 86		Authorized officer Kerstin Boije Janson Telephone No. +46 8 782 25 00

Form PCT/ISA/210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT
Information on patent family members

26/08/93

International application No.
PCT/SE 93/00604

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB-A- 1099293	17/01/68	CH-A- 431821 DE-A- 1492478 NL-A- 6508278	15/09/67 13/02/69 10/01/66
JP-A2- 57153873	22/09/82	NONE	
WO-A1- 9219287	12/11/92	AU-A- 1665592	21/12/92

Form PCT/ISA/210 (patent family annex) (July 1992)